

MS POLYMER ADHESIVE

TOVCOL MS START

APPEARANCE
Dense paste

DENSITY
1.7kg/litre

PACKAGING
15kg buckets

COLOURS AVAILABLE
Light wood, Dark wood

SPECIFICATIONS

Technicaldataat20°C - 60%r.u.

OPEN TIME	**40 - 60 minutes**
BLOCKING TIME	**6 – 8 hours**
LIGHT TRAFFIC	**6 – 8 hours**
SANDING	**2 – 3 days**
YIELD	**700 – 1200g/m^2 – 8mm trowel**
SHEAR STRENGTH	**1.2N/mm^2 | UNI EN 14293 – Elastic glue**
APPLICATION TEMPERATURE	**From +10°C to +35°C**
STORAGE	**12 months in original packaging at temp > 10°C**
TOOL CLEANING	**Solvente di Lavaggio S/23, if hardened, only mechanically**
CLEANING OF RESIDUE ON THE FLOOR	**When freshly applied, use Stripcoll to remove residue. Once dry, residue can be removed manually.**